

48

PE 7030AG – Black

Environnement Massif Central

Donnons vie à vos déchets !

	<u>Property</u>	<u>Value</u>	<u>Standard</u>
PE 7030AG - Black	MFI (190°C/60s/5.00kg)	1 - 1.4 g/10min	ISO 1133
	Density	0.955 - 0.970 g/cm ³	
	Filler content (Method A)		ISO 3451-1
	Moisture rate	< 0,02%	
	Tensile stress at yield (50 mm/min)	22.4 Mpa	ISO 527
	Elongation at yield (50 mm/min)	10,00%	ISO 527
	Tensile modulus (1 mm/min)	905 Mpa	ISO 527
	Elongation at break (50 mm/min)	120 %	ISO 527
	Flexural modulus (2 mm/min)	875 Mpa	ISO 178
	Impact resistance (Charpy 2 joules)	> 12 Kj/m ²	ISO 179-1/1eA

ISO 9001
ISO 14001
BUREAU VERITAS
Certification



48

PE 7030AG – Grey

Environnement Massif Central

Donnons vie à vos déchets !

	<u>Property</u>	<u>Value</u>	<u>Standard</u>
PE 7030AG - Grey	MFI (190°C/60s/5.00kg)	1.0 - 2.0 g/10min	ISO 1133
	Density	0,955 - 0.970 g/cm ³	
	Filler content (Method A)		ISO 3451-1
	Moisture rate	< 0,02%	
	Tensile stress at yield (50 mm/min)	22.4 Mpa	ISO 527
	Elongation at yield (50 mm/min)	10,00%	ISO 527
	Tensile modulus (1 mm/min)	905 Mpa	ISO 527
	Elongation at break (50 mm/min)	120 %	ISO 527
	Flexural modulus (2 mm/min)	875 Mpa	ISO 178
	Impact resistance (Charpy 2 joules)	> 12 Kj/m ²	ISO 179-1/1eA

ISO 9001
ISO 14001
BUREAU VERITAS
Certification

